


Product Information	SP20M₂40300B	 Sam Polymer Bonyan
---------------------	--------------------------------	--

Product Description

SP20M₂40300B is a black Copolypropylene reinforced by 40% Talc.

Property	Test Method (ASTM)	Test Condition	Value	Unit
PHYSICAL				
Density	D792	23°C	1.25	g/cm ³
Melt Flow Rate (MFR)	D1238	230 °C, 2.16 Kg	7.5	g/10min
MECHANICAL				
Tensile Strength, Yield	D638	23°C	18	MPa
Tensile Elongation, Yield	D638	23°C	2.0	%
Flexural Strength	D790	23°C	61	MPa
Flexural Modulus	D790	23°C	3250	MPa
Izod Impact Strength	D256	notched, 23°C	6.0	KJ/m ²
THERMAL				
Vicat Softening Temperature	D1525	50 N, heating rate 50 °C/h	142	°C
Heat Deflection Temperature (HDT)	D648	0.45 Mpa	135	°C
		1.80 Mpa	75	°C

Processing Guidelines

Predrying	Drying Time: 2-4 h	Drying Temperature: 80-100 °C
------------------	--------------------	-------------------------------

Injection Molding	Cylinder Temperature (°C)	Mold Temperature (°C)	Injection Speed	Injection Pressure (MPa)
	200-220	30-50	Medium	40-130

All above mentioned data are typical values and not to be construed as real specifications. Users should confirm results by their own tests.